

FINE BUILDING SAND

Fine builing sand for the preparation of fine plasters/renders

- Nature quartz sand
- ▶ 100% washed, harmlessness
- ▶ Sieved and correct grain-size distribution
- ▶ Remarkably mechanical properties
- ▶ Biologically safe
- ▶ Naturally moist



PRODUCT	Fine Quartz sand, grain size 0,063-1,0 mm.
DESCRIPTION	rine Quartz sand, grain size 0,003-1,0 mm.

FIELD OF USE For prepartion of fine plasters/renders for finishing exteriors as well as interior wall surfaces. Naturally moist.

PRODUCT • Nature quartz sand

- PROPERTIES 100% washed, harmlessness
 - Sieved and correct grain-size distribution
 - Remarkably mechanical properties
 - Biologically safe
 - Naturally moist

PRODUCT DATA		
BASIC INFORMATION	Appearance	Yellow sand
	Packing	25 kg v PE bag / 1000 kg (40x25 kg) on palette Bulk
	Storage and expiration date	Unlimited from date of production if stored properly in undamaged original sealed packaging in dry and cool conditions. Date of production is printed or packaging.





Grain Size	0,063 - 1,0 mm
Hardness (Mohs)	7
Ignition loss	< 0,03 %
Sintering point	> 1500 °C
Softening point	> 1720 °C
Uncompacted bulk density	1320 kg/m³ according to grain size
Compacted bulk density	1480 kg/m ³ according to grain size
Moisture	up to 4 %

PROPERTIES

SiO ₂	> 99 %
Fe ₂ O ₃	0,297 %
Al_2O_3	0,658 %
TiO ₂	0,032 %
CaO	0,041 %
MgO	0,027 %
P ₂ O ₅	0,009 %
K ₂ O	0,104 %

CHEMICAL COMPOSITION

INSTRUCTIONS FOR USE

CONSUMPTION Depending on the mixing ratio.

LIMITATIONS

Data source: All technical data in this technical sheet was obtained by laboratory research. Actual data may differ due to different working conditions.

Local restrictions: Due to specific local regulations the installed product can differ from country to country. For exact instructions for use a country specific technical sheet should be obtained.

PROOFS

NORMS/STANDARDS In accordance with EN 13139:2002, report no.: P 171-AGR-04; Igmat d.d. Ljubljana - Polje, Slovenia.





SAFETY DATA

More data on storage, handling and use of product can be found in the safety sheet which contains safety, toxicological and ecological data. Warnings on the original packaging should also be considered.

LEGAL BASE

Information and recommendations related to use of KEMA products are presented in good faith and believed to be correct. The later is based on our knowledge and experience with the products. Information is supplied upon the condition that products are stored and used according to the recommendations and the persons receiving the same will make their own determination as to its suitability for their purposes prior to use. No representations or warranties, either expressed or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which information refers. In no event will KEMA be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to the use any product, process, equipment or formulation in conflict with any patent, and KEMA makes no representation or warranty, expressed or implied that the use thereof will not infringe any patent. All orders fall under current sales and supply conditions. The user should always check the latest technical sheet available upon demand.

Murexin Ltd, Suite 4 Banters House, Banters Lane, Great Leigh's, Essex, CM3 1QX, UK

E www.murexin-uk.com