

KEMA Puconci d.o.o., Puconci 109, 9201 Puconci, Slovenija T: +386 (0)2 545 95 00, F: +386 (0)2 545 95 10 Technical consulting: +386 (0)2 545 95 28, +386 (0)2 545 95 73 I: www.kema-on.net | E: info@kema.si

KEMATERM PL-TOP

Ready-to-use pasty synthetic-resin top coat



PRODUCT DESCRIPTION	Ready-to-use pasty synthetic-resin, white or coloured thin-layer cover coat as floating and set with scraped or corrugated structure for outside and inside applications. Can be processed manually and by machine.		
	Aveilable in scratch (K) structure in grain size of 1,5 mm (1,5 K) and 2 mm (2K).		
Field of use	Protection and design of facades and internal wall surfaces on mineral plasters, on concrete, for rework on organically bound compounds and plasters, as final coat for the Kema thermo facade systems. Prior coating with KEMATERM GRUND 210 is obligatory.		
	KEMATERM PL-TOP is suitable on nexts surfaces: - Backing plaster for the thermal insulating composite system EPS - Lime/cement plasters, concrete - Mineral, silicate and water-base paint and plasters with good adhesion properties. - Gypsum based plasters (test it on trial surface)		
Product properties	 Weather-resistant Highly hydrophobic Water vapour permeable, washable Easy to work with 		
PRODUCT DATA			
Basic information			
	Appearance	Pasty resin compound in colour tones with last description number 9	
	Packing	25 kg bucket / 600 kg (24x25 kg) on pallet e 12 months from date of production if stored properly in undamaged original sealed packaging in dry and cool conditions. Date of production is printed on packaging.	
	Storage and expiration date		
Technical data			
	Type of product Largest grain		Synthetic binders, mineral fillers, colorants, additives, water.
			2.0 mm
	Apparent density		approx. 1.8 kg/dm ³
	Thermal conductivity λ		approx. 0.70 W/mK
	Vapour diffusion resistance coefficient $\boldsymbol{\mu}$		approx. 50
	Water absorption coefficient (w value)		< 0,20 kg/m²×t0,5
	sd value		0.1 m (layer thickness of 2 mm)
	Colours		colours with last description number 9



KEMA Puconci d.o.o., Puconci 109, 9201 Puconci, Slovenija T: +386 (0)2 545 95 00, F: +386 (0)2 545 95 10 Technical consulting: +386 (0)2 545 95 28, +386 (0)2 545 95 73 I: www.kema-on.net | E: info@kema.si

Structure of coats

1 x KEMATERM GRUND 210 1 x KEMATERM PL-TOP

INSTRUCTIONS FOR USE Consumption approx. 3,2 kg/m² Base The base surface must satisfy the following requirements: clean, dry, free of frost, free of dust, not water-repellent, free of efflorescence, supporting and free os loose particles. **Base preparation** Pre-treatment of the base: Consolidate chalking or sanding surfaces - Mechanically remove sinter skin - Remove forming oil residues from concrete with hot steam or commercially available special forming oil removers - Clean dirty surfaces Treat base surfaces infested with algae with speacial agent
 Remove weathered coats of paint with bad adhesion properties by mechanical means - Coat damaged and cracked mineral surfaces with stopper Mix ratio Kematerm PL-TOP is ready-to-use compound, so nothing is allowed to add. Mix time Mix KEMATERM PL-TOP top coat thoroughly before application Mix tool For mixing use a a electric stirrer. After the KEMATERM GRUND 210 has been left to dry for at least 24 hours, KEMATERM PL-TOP is applied. Apply the final coat to the entire surface with trowel or spray it on with a suitable fining plaster machine, then screed to grain thickness and spread thin with float immediately after application. Work evenly and without interruption. Installation Tool For application we choose stainless steel trowel and for spreading a plastic plasterers float. **Cleaning of tool** Clean tools immediately after the use before adhesive hardens. Hardened material on tools can only be removed mechanically. LIMITATIONS Base temperature +5°C min./ +30°C max. Air temperature +5°C min./ +30°C max. Material temperature +5°C min./ +30°C max. Warnings Protect facade against direct solar irradiation, rain or strong wind (for instance with scaffolding netting) High relative humidity and low temperatures can prolong the drying time considerably and cause irregular colour changes A uniform colour appearance can only be guaranteed if the products all come from a single batch. The development of the colour tone can be greatly influenced by the conditions of the base, the temperature and the air humidity Kematern PL-G can be adjusted on request to inhibit algae growth (this has a preventive and delaying effect, however, the non-appearance of algae cannot be guaranteed). If several batches are used, always ensure that they are mixed together before starting work. If used on thermal insulating composite systems, the brightness reference value must not be lower than 30. Do not mix with other coating substances. Can be painted over with KEMACOLOR G organic paint and KEMACOLOR X silicone paint. All base surfaces must be pre-treated with KEMATERM GRUND 210 primer. (Resting period: at least 24 hours) KEMATERM PL-TOP is not suitable on nexts surfaces: fresh lime finishes, plastics and resins, resin and oil films, dstemper, whitewash, gypsum plasters Recommendation: Remains of the unhardened/unset material have to be removed in accordance with the legislation. Data source: All technical data in this technical sheet was obtained by laboratory research. Actual data may differ due to different working conditions Local restrictions: Due to specific local regulations the installed product can differ from country to country. For exact instructions for use a country specific technical sheet should be obtained. Protect your eyes and skin as well as the surroundings of the surfaces to be coated in particular glass, ceramic, clinker, natural stone, paint and SAFETY DATA metal surfaces. If applicable, remove silicone plaster splashes by rising the affected areas with a lot of water, do not wait until the plaster dires out and gets hard. S phrases: S 2 Keep away from children. S 24 Avoid contact with the skin. S 25 Avoid contact with eyes. S 37 Wear suitable gloves **OTHER INFORMATION** Quality assurance: Internal quality assurance is provided by our factory laboratories. Our system of regular production checks is externally controlled by an approved institute. LEGAL BASE Information and recommendations related to use of KEMA products are presented in good faith and believed to be correct. The later is based on our knowledge and Information and recommendations related to use of KEMA products are presented in good faith and believed to be correct. The later is based on our knowledge and experience with the products. Information is supplied upon the condition that products are stored and used according to the recommendations and the persons receiving the same will make their own determination as to its suitability for their purposes prior to use. No representations or warranties, either expressed or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which information refers. In no event will KEMA be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to the use any product, process, equipment or formulation in conflict with any patent, and KEMA makes no representation or warranty, expressed or implied that the use thereof will not infringe any patent. All orders fall under current sales and supply conditions. The user should always check the latest technical sheet available upon demand.