

KEMA d.o.o., Puconci 393, 9201 Puconci, Slovenija T: +386 (0)2 545 95 00, F: +386 (0)2 545 95 10 Technical consulting: +386 (0)2 545 95 28, +386 (0)2 545 95 73 I: www.kema-on.net | E: info@kema.si Label: TL_Term_PL_VIVA Issue: July 2008 Revision: August 2015 ID: 421

TECHNICAL DATA SHEET

KEMATERM PL-VIVA

Ready-to-use intensive coloured pasty synthetic-resin top coat



PRODUCT DESCRIPTION

Ready-to-use pasty synthetic-resin thin-layer cover coat as floating and set with scraped or corrugated structure for outside and inside applications, with brilliant colouration. Can be processed manually and by machine.

Available in scratch (K) structures and next grain sizes:

- 1,5 K
- 2 K
- 3 K

Field of use

Protection and decoration of facades and internal wall surfaces on mineral plasters and stoppers, on concrete, for rework on organically bound stoppers and plasters, as final coat for the Kema thermo façade systems. Prior coating with KEMATERM GRUND 210 is obligatory.

KEMATERM PL-G is suitable on nexts surfaces:

- Backing plaster for the thermal insulating composite system EPS
- Lime/cement plasters, concrete
- Mineral, silicate and water-base paint and plasters with good adhesion properties.
- properties.
 Gypsum based plasters (test it on trial surface)

Product properties

- · Brilliant colouration
- Weather-resistant
- Highly hydrophobic
- Water vapour permeable, washable
- High mechanical stress and load resistance
- Easy to work with

PRODUCT DATA

Basic information

Appearance	Pasty resin compound in 30 colour tones
Packing	25 kg bucket / 600 kg (24x25 kg) on pallet
Storage and expiration date	12 months from date of production if stored properly in undamaged original sealed packaging in dry and cool conditions. Date of production is printed on packaging.

Technical data

Type of product	Synthetic binders, mineral fillers, colorants, additives, water.		
Largest grain	1.5/2.0/3.0 mm		
Apparent density	approx. 1.8 kg/dm³		
Thermal conductivity λ	approx. 0.70 W/mK		
Vapour diffusion resistance coefficient µ	approx. 110-140		
Water absorption coefficient (w value)	< 0,15 kg/m²×t0,5		



KFMA d.o.o. Puconci 393, 9201 Puconci, Slovenija T: +386 (0)2 545 95 00, F: +386 (0)2 545 95 10 Technical consulting: +386 (0)2 545 95 28, +386 (0)2 545 95 73 I: www.kema-on.net | E: info@kema.si

I abel: TL_Term_PL_VIVA July 2008 Issue: Revision: August 2015

sd value	0.22 – 0.28 m (layer thickness of 2 mm)
Colours	30 colours (special colours on request)
Adhesive strenght	> 3 MPa

Structure of coats

On generally base:

1 x KEMATERM GRUND 210

1 x KEMATERM PL-VIVA

On repaired mineral base:

2 x KEMATERM GRUND 210 1 x KEMATERM PL-VIVA

INSTRUCTIONS FOR USE

Consumption

Consumption depends of structure and grain size.

Grain size	1,5K	2K	3K	
Consumption (kg/m²)	2,5	3,1	4,1	

^{*-}including with holes

Base

The base surface must satisfy the following requirements: clean, dry, free of frost, free of dust, not water-repellent, free of efflorescence, supporting and free os loose particles.

Base preparation

Pre-treatment of the base:

- Consolidate chalking or sanding surfaces
- Mechanically remove sinter skin
- Remove forming oil residues from concrete with hot steam or commercially available special forming oil removers
- Clean dirty surfaces
- Treat base surfaces infested with algae with speacial agent
- Remove weathered coats of paint with bad adhesion properties by mechanical means
- Coat damaged and cracked mineral surfaces with stopper

Mix ratio

Kematerm PL-VIVA is ready-to-use compound, so nothing is allowed to add.

Mix time

Mix KEMATERM PL-VIVA top coat thoroughly before application

Mix tool

For mixing use a a electric stirrer.

Installation

After the KEMATERM GRUND 210 has been left to dry for at least 24 hours, KEMATERM PL-VIVA is applied. Apply the final coat to the entire surface with trowel or spray it on with a suitable fining plaster machine, then screed to grain thickness and spread thin with float immediately after application. Work evenly and without interruption.

Tool

For application we choose stainless steel trowel and for spreading a plastic plasterers float.

Cleaning of tool

Clean tools immediately after the use before adhesive hardens. Hardened material on tools can only be removed mechanically

LIMITATIONS

Base temperature

+5°C min./ +30°C max. +5°C min./ +30°C max.

Air temperature Material temperature

+5°C min./ +30°C max.

Warnings

- Protect facade against direct solar irradiation, rain or strong wind (for instance with scaffolding netting).
- High relative humidity and low temperatures can prolong the drying time considerably and cause irregular colour
- changes.

 A uniform colour appearance can only be guaranteed if the products all come from a single batch.

 The development of the colour tone can be greatly influenced by the conditions of the base, the temperature and the air
- Kematerm PL-G can be adjusted on request to inhibit algae growth (this has a preventive and delaying effect, however, the non-appearance of algae cannot be guaranteed). If several batches are used, always ensure that they are mixed together before starting work.
- If used on thermal insulating composite systems, the brightness reference value must not be lower than 30
- Do not mix with other coating substances.
 Can be painted over with KEMACOLOR G organic paint, KEMACOLOR VIVA organic paint and KEMACOLOR X silicone paint.
- All base surfaces must be pre-treated with KEMATERM GRUND 210 primer. (Resting period: at least 24 hours)
- KEMATERM PL-VIVA is not suitable on nexts surfaces: fresh lime finishes, plastics and resins, resin and oil films, dstemper, whitewash, gypsum plasters

Recommendation: Remains of the unhardened/unset material have to be removed in accordance with the legislation.

Data source: All technical data in this technical sheet was obtained by laboratory research. Actual data may differ due to different working conditions

Local restrictions: Due to specific local regulations the installed product can differ from country to country. For exact instructions for use a



KEMA d.o.o., Puconci 393, 9201 Puconci, Slovenija T: +386 (0)2 545 95 00, F: +386 (0)2 545 95 10 Technical consulting: +386 (0)2 545 95 28, +386 (0)2 545 95 73 I: www.kema-on.net | E: info@kema.si Label: TL_Term_PL_VIVA Issue: July 2008 Revision: August 2015

country specific technical sheet should be obtained.

SAFETY DATA

Protect your eyes and skin as well as the surroundings of the surfaces to be coated in particular glass, ceramic, clinker, natural stone, paint and metal surfaces. If applicable, remove silicone plaster splashes by rising the affected areas with a lot of water, do not wait until the plaster dires out and gets hard.

S phrases: S 2 Keep away from children. S 24 Avoid contact with the skin. S 25 Avoid contact with eyes. S 37 Wear suitable gloves

OTHER INFORMATION

Quality assurance:

Internal quality assurance is provided by our factory laboratories. Our system of regular production checks is externally controlled by an approved institute.

LEGAL BASE

Information and recommendations related to use of KEMA products are presented in good faith and believed to be correct. The later is based on our knowledge and experience with the products. Information is supplied upon the condition that products are stored and used according to the recommendations and the persons receiving the same will make their own determination as to its suitability for their purposes prior to use. No representations or warranties, either expressed or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which information refers. In no event will KEMA be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to the use any product, process, equipment or formulation in conflict with any patent, and KEMA makes no representation or warranty, expressed or implied that the use thereof will not infringe any patent. All orders fall under current sales and supply conditions. The user should always check the latest technical sheet available upon demand.